



Typical Values

MAPEX NYLON ENGINEERING PLASTICS

Properties	UNIT	Test Method	Mapex A0620NH B06
Mechanical			
抗張強度 Tensile Str, Yield	Psi(Mpa)	D-638	19000(131)
斷裂伸長率 Tensile Elongation, Break	%	D-638	2.5(2.5)
彎曲強度 Flexural Strength	Psi(Mpa)	D-790	29000(200)
彎曲彈性率 Flexural Modulus	Psi(Mpa)	D-790	1250000(8600)
IZOD衝擊強度 Izod Impact Strength, Notched	ft.lb/in (J/m) 23°C -30°C	D-256	1.60(8.56) -
硬度 Rockwell Hardness	R-Scale	D-785	-
Thermal			
融點 Melting Point	°C	D-789	260-265
熱變形溫度 Heat Deflection Temperature	°C 66 psi(0.45Mpa) 264 psi(1.82Mpa)	D-648	- 240
線膨脹係數 Coefficient of Thermal Expansion	E-5 1/°C	D-696	-
熾熱電線耐燃試驗 Glow Wire Test	°C	IEC 695-2-1	-
Electrical			
介電強度 Dielectric Strength	kv/mm	D-149	-
體積電阻 Volume Resistivity	ohm-cm	D-257	-
耐電弧 Arc Resistance	Sec	D495	-
Other			
比重 Specific Gravity	-	D-792	1.39-1.42
流動指數 Melt Flow Index	g/10min (275°C/5Kg)	D-1238	20-70
成型收縮率 Mold Shrinkage, Flow	% 3mm	D-955	0.25-0.40
吸水率 Water Absorption	% 23°C, 24hr	D-570	-
Flammability			
燃燒性 Flammability	1/8" 1/16" 1/32"	UL-94	- - V0
附註 Remark	Polyamide 66 30% Flame Retardant & Glass Fiber Reinforced Grade, Black Color, Chloride & Bromide-Free, RoHS Certification		

*Typical properties can be subject to change without further notice.

ISO9001 / ISO14001 / IECQ QC080000 ASSURANCE

GINAR TECHNOLOGY CO., LTD.
Marketing Communications Department TAIWAN
Phone +886-3-3868820 Fax +886-3-3863587
Http: // www.ginar.com.tw
E-mail: ginar@ ginar.com.tw

單位換算	抗張強度, 彎曲強度, 彎曲彈性率	IZOD 衝擊強度
	1psi=0.0703 kg/cm ²	1 ft.lb/in =5.45 kg.cm/cm
	1Mpa=10.2 kg/cm ²	1J/m=0.102 kg.cm/cm

Date Issued: 2012/10/23
#