

ALTECH PA66 A 2015/109 GF15

(Last update: 27.01.2014)

Base Polymer	Polyamide 66
Filler/Additive System	15 % glass fibres
Special Features	heat ageing stabilisation,easy release (demoulding),good flow
Typical Applications	various

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer,for 2-12 h,dependant on moisture content,0,15 % max. moisture content
Processing Conditions	injection moulding melt temperature 280-300 °C,injection moulding mould temperature 80-120 °C
Storage	dry, protected from light,not above 30°C

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural modulus	5300	MPa	ISO 178
Flexural strength	180	MPa	ISO 178
Tensile modulus	5500	MPa	ISO 527-1/-2
Tensile elongation at break	2.5	%	ISO 527-1/-2
Charpy notched impact 1eA	5	kJ/m²	ISO 179/1eA
Impact strength Charpy 1eU	30	kJ/m²	ISO 179/1eU
Thermal Properties			
Vicat B50	252	°C	ISO 306
HDT / A (1,8 MPa)	244	°C	ISO 75-1/-2
Physical Properties			
Density	1230	kg/m³	ISO 1183

These are guide values and not a specification. Any information given on the chemical and physical characteristics of our products, including technical advice on applications whether verbally, in writing or by testing the product, is given to the best of our knowledge. It does not exempt the buyer from carrying out his own investigations and tests in order to ascertain the products' specific suitability for the purpose intended.

The buyer is solely responsible for the application, utilisation and processing of the products, and must observe the laws and government regulations and the consequential rights of any third party.

The test values mentioned are guide values only and not binding minimum or maximum figures. These test values have been determined on standardised test specimen and they can be affected by pigmentation, mould design and processing conditions.

ALBIS expressly advises against the use of this product in any medical, pharmaceutical or diagnostic application. At all times our Conditions of Sale apply.