



MAPEX

NYLON ENGINEERING PLASTICS

Properties	UNIT	Test Method	Mapex N0320FN B01
Mechanical			
抗張強度 Tensile Str.Yield	Psi(Mpa)	D-638	15000(103.4)
斷裂伸長率 Tensile Elongation,Break	%	D-638	1.5-2.0
彎曲強度 Flexural Strength	Psi(Mpa)	D-790	24000(165.5)
彎曲彈性率 Flexural Modulus	Psi(Mpa)	D-790	910000(6275)
IZOD衝擊強度 Izod Impact Strength,Notched	ft.lb/in (J/m) 23°C -30°C	D-256	1.25(66.69) -
硬度 Rockwell Hardness	R-Scale	D-785	-
Thermal			
融點 Melting Point	°C	D-789	220
熱變形溫度 Heat Deflection Temperature	°C 66 psi(0.45Mpa) 264 psi(1.82Mpa)	D-648	- 200-210
線膨脹係數 Coefficient of Thermal Expansion	E-5 1/°C	D-696	-
熾熱電線耐燃試驗 Glow Wire Test	°C	IEC 695-2-1	-
Electrical			
介電強度 Dielectric Strength	kv/mm	D-149	-
體積電阻 Volume Resistivity	ohm-cm	D-257	-
耐電弧 Arc Resistance	Sec	D495	-
Other			
比重 Specific Gravity	-	D-792	1.47
流動指數 Melt Flow Index	g/10min (275°C/5Kg)	D-1238	130-150
成型收縮率 Mold Shrinkage , Flow	% 3mm	D-955	0.20-0.40
吸水率 Water Absorption	% 23°C,24hr	D-570	-
Flammability			
燃燒性 Flammability	1/8" 1/16" 1/32"	UL-94	- - V0

附註 Remark Polyamide 6, 18% Glass Fiber Reinforced, 1/32"V0 Flame Retardant Grade, Black Color, RoHS certification

*Typical properties can be subject to change without further notice.

ISO9001 / ISO14001 / IECQ QC080000 ASSURANCE

GINAR TECHNOLOGY CO., LTD.
Marketing Communications Department TAIWAN
Phone +886-3-3868820 Fax +886-3-3863587
Http: // www.ginar.com.tw
E-mail:ginar@ ginar.com.tw

單位換算	抗張強度, 彎曲強度, 彎曲彈性率 1psi=0.0703 kg/cm ² 1Mpa=10.2 kg/cm ²	IZOD 衝擊強度 1 ft.lb/in =5.45 kg.cm/cm 1J/m=0.102 kg.cm/cm
------	---	---