

Makrolon 2405

General purpose grades / Low viscosity

Global grade; MVR (300 °C/1.2 kg) 19 cm³/10 min; General purpose; Low viscosity; Easy release; Injection molding - Melt temperature 280 - 320 °C; Available in transparent, translucent and opaque colors

ISO Shortname

ISO 7391-PC,MR,(,)-18-9

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Melt mass-flow rate	300 °C; 1.2 kg	g/10 min	ASTM D1238	20
Mold shrinkage, flow/cross to flow		in/in	ASTM D955	0.005 - 0.007
Mechanical properties (23 °C/50 % r. h.)				
Tensile modulus	1 mm/min	lb/in²	ASTM D638	350000
Tensile stress at yield	-	lb/in²	ASTM D638	9400
Tensile elongation at yield	-	%	ASTM D638	6.0
Tensile elongation at break	-	%	ASTM D638	115
Tensile stress at break	-	lb/in²	ASTM D638	8700
Izod notched impact strength	73 °F, 0.125 in	ft·lb/in	ASTM D256	14
Flexural modulus	-	lb/in²	ASTM D790	340000
Flexural stress at 5 % strain		lb/in²	ASTM D790	12000
Rockwell hardness		M Scale	ASTM D785	75
Rockwell hardness		R Scale	ASTM D785	120
Thermal properties				
Deflection temperature under load, Unannealed	264 psi; 0.250 in	°F	ASTM D648	259
Deflection temperature under load, Unannealed	66 psi; 0.250 in	°F	ASTM D648	273
Vicat softening temperature	50 N, 50 °C/h	°F	ASTM D1525	291
Coefficient of linear thermal expansion, flow/cross-flow		in/in/°F	ASTM D696	3.34 E-05
UL94 Flame Class	Thickness tested: 1.5 mm	Class	UL 94	V-2
UL94 Flame Class	Thickness tested: 3.0 mm	Class	UL 94	HB
UL94 Flame Class	Thickness tested: 6.0 mm	Class	UL 94	HB
Oxygen index		%	ASTM D2863	28
Thermal conductivity		Btu·in/(h·ft²·°F)	ASTM C177	1.39
Specific heat		Btu/(lb·°F)	ASTM D2766	0.28
Relative temperature index (Tensile impact strength)	Thickness tested: 1.5 mm	°C	UL 746B	115
Relative temperature index (Tensile strength)	Thickness tested: 1.5 mm	°C	UL 746B	125
Relative temperature index (Electric strength)	Thickness tested: 1.5 mm	°C	UL 746B	125
Electrical properties (23 °C/50 % r. h.)				
Dissipation factor, Tinfoil electrodes	60 Hz	-	ASTM D150	0.0008
Dissipation factor, Tinfoil electrodes	1 MHz	-	ASTM D150	0.01
Dielectric constant, Tinfoil electrodes	60 Hz	-	ASTM D150	3.0
Dielectric constant, Tinfoil electrodes	1 MHz	-	ASTM D150	2.9
Volume resistivity, Tinfoil electrodes		Ohm·m	ASTM D257	1.0 E+14
Surface resistivity		Ohm	ASTM D257	1.0 E+16
Electrical strength	Short time under oil at 73 °F	V/mil	ASTM D149	810
Other properties (23 °C)				
Water absorption	73 °F; immersion to saturation	%	ASTM D570	0.30
Water absorption	73 °F; immersion 24 h	%	ASTM D570	0.12
Density		lb/in³	ASTM D792	0.043
Specific volume		in³/lb	ASTM D792	23.1
Specific gravity		-	ASTM D792	1.2
Material specific properties				
Refractive index		-	ASTM D542	1.586
Luminous transmittance (clear transparent materials)	0.125 in	%	ASTM D1003	88
Haze for transparent materials	0.125 in	%	ASTM D1003	< 0.8



Makrolon 2405

Disclaimer

Standard Disclaimer

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee, and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Typical Properties

Property data is provided as general information only. Property values are approximate and are not part of the product specifications.

Flammability

Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

Health and Safety

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling Bayer products mentioned in this publication. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets (MSDS) and product labels. Consult your Bayer Polymers representative or contact the Bayer Product Safety and Regulatory Affairs Department in Pittsburgh, Pennsylvania. For materials that are not Bayer products, appropriate industrial hygiene and other safety precautions recommended by their manufacturer(s) must be followed.

Publisher: Global Innovations - Polycarbonates

Bayer MaterialScience AG,

D-51368 Leverkusen,

www.bayermaterialscience.com

pcs-info@bayermaterialscience.com