

Product Overview

The products in the following table meet these criteria

Generic: PC

Product	Generic	Melt Mass Flow Rate (g/10 min)	Density (g/cm ³)
CALIBRE™ 200-15	PC	15 (300°C/1.2 kg, ASTM D1238); 15 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183); 1.20 (ISO 1183)
CALIBRE™ 302-15	PC	15 (300°C/1.2 kg, ASTM D1238); 15 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183); 1.20 (ISO 1183)
EMERGE™ PC 8702-5	PC	5.0 (300°C/1.2 kg, ISO 1133)	1.33 (ISO 1183)
EMERGE™ PC 4202-8	PC	8.0 (300°C/1.2 kg, ASTM D1238)	1.36 (ASTM D792)
EMERGE™ PC 4310-10	PC	10 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4310-15	PC	15 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4310-22	PC	22 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4310-6	PC	6.0 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4330-10	PC	10 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4330-15	PC	15 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4330-22	PC	22 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4330-6	PC	6.0 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4701-13	PC	13 (300°C/1.2 kg, ASTM D1238)	1.27 (ASTM D792)
EMERGE™ PC 8600-10	PC	10 (300°C/1.2 kg, ASTM D1238); 10 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183)
EMERGE™ PC 8600-20	PC	20 (300°C/1.2 kg, ISO 1133)	1.20 (ISO 1183)
CELEX™ 350	PC	10 (300°C/1.2 kg, ASTM D1238)	1.58 (ASTM D792)
CELEX™ 310HF	PC	19 (300°C/1.2 kg, ASTM D1238)	1.24 (ASTM D792)
CELEX™ 320.N	PC	6.0 (300°C/1.2 kg, ASTM D1238)	
CELEX™ 330AD	PC	12 (256°C/3.8 kg, ASTM D1238)	1.43 (ASTM D792)
CELEX™ 5200HF	PC	19 (230°C/3.8 kg, ASTM D1238)	1.18 (ASTM D792)
EMERGE™ PC 8702-15 (AP)	PC	15 (300°C/1.2 kg, ASTM D1238)	1.33 (ASTM D792)
EMERGE™ PC 8701	PC	8.0 (300°C/1.2 kg, ISO 1133)	1.28 (ISO 1183)
CELEX™ 3600-10	PC	10 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
CELEX™ 3600-20	PC	20 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 8600-7	PC	7.0 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4902	PC	25 (300°C/1.2 kg, ASTM D1238)	1.30 (ASTM D792)
EMERGE™ PC 8330	PC	22 (300°C/1.2 kg, ISO 1133)	1.20 (ISO 1183)
CELEX™ 310HF.B	PC	18 (300°C/1.2 kg, ASTM D1238)	1.26 (ASTM D792)
EMERGE™ PC 8701HH	PC	8.0 (300°C/1.2 kg, ISO 1133)	1.28 (ISO 1183)
EMERGE™ PC 8230-10	PC	10 (300°C/1.2 kg, ISO 1133)	1.20 (ISO 1183)

Product Overview

Product	Generic	Melt Mass Flow Rate (g/10 min)	Density (g/cm ³)
CELEX™ 310HF.M	PC	18 (300°C/1.2 kg, ASTM D1238)	1.28 (ASTM D792)
EMERGE™ PC 8230-20	PC	20 (300°C/1.2 kg, ISO 1133)	1.20 (ISO 1183)
EMERGE™ PC 4350	PC	15 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 4701-15	PC	15 (300°C/1.2 kg, ASTM D1238)	1.27 (ASTM D792)
CALIBRE™ 340 TNIR	PC	8.0 (300°C/1.2 kg, ISO 1133)	1.20 (ISO 1183)
EMERGE™ PC 8310-10 (AP)	PC	10 (300°C/1.2 kg, ASTM D1238)	1.20 (ASTM D792)
EMERGE™ PC 8900	PC	13 (300°C/1.2 kg, ASTM D1238)	1.21 (ASTM D792)
EMERGE™ PC 8702-10	PC	10 (300°C/1.2 kg, ASTM D1238)	1.33 (ASTM D792)
EMERGE™ PC 8731	PC	13 (300°C/1.2 kg, ASTM D1238)	1.28 (ASTM D792)
CALIBRE™ MEGARAD™ 2091-15	PC	15 (300°C/1.2 kg, ASTM D1238); 15 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183)
CALIBRE™ 2061 HD 15	PC	15 (300°C/1.2 kg, ASTM D1238); 15 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183)
CALIBRE™ MEGARAD™ 2081 HD-15 2	PC	15 (300°C/1.2 kg, ASTM D1238); 15 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183)
EMERGE™ PC 4903	PC	12 (300°C/1.2 kg, ASTM D1238)	1.46 (ASTM D792)
EMERGE™ PC 8410-7 LT	PC	7.0 (300°C/1.2 kg, ISO 1133)	1.20 (ISO 1183)
EMERGE™ PC 8430-7 LT	PC	7.0 (300°C/1.2 kg, ISO 1133)	1.20 (ISO 1183)
CALIBRE™ 5201-12	PC	12 (300°C/1.2 kg, ASTM D1238); 12 (300°C/1.2 kg, ISO 1133)	1.36 (ASTM D792); 1.36 (ISO 1183)
CALIBRE™ 603-2	PC	1.8 (300°C/1.2 kg, ASTM D1238); 1.8 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183)
EMERGE™ PC 4330ECO	PC	23 (300°C/1.2 kg, ASTM D1238)	1.26 (ASTM D792)
Experimental XQ 83625.00	PC	12 (230°C/3.8 kg, ASTM D1238)	1.40 (ASTM D792)
CALIBRE™ 2060-3	PC	3.5 (300°C/1.2 kg, ASTM D1238); 3.5 (300°C/1.2 kg, ISO 1133)	1.20 (ASTM D792); 1.20 (ISO 1183)

Product
Stewardship

Customer
Notice

Notice Regarding
Medical Application
Restrictions

Disclaimer

Responsible Care®

Additional
Information

Styron LLC, Styron HoldCo B.V., and subsidiaries (“Styron”) have a fundamental concern for all who make, distribute, and use its products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health and environmental information on our products to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Styron products – from the initial concept and research, to manufacture, use, sales, disposal and recycle of each product

Customers are responsible for reviewing their manufacturing processes and their applications of Styron products from the standpoint of human health and environmental quality to ensure that Styron products are not used in ways for which they are not suitable. Styron personnel are available to answer questions and to provide reasonable technical support. Styron product literature, including safety data sheets, should be consulted prior to the use of Styron products. Current safety data sheets are available from Styron.

Styron requests that customers considering the use of Styron products in medical applications notify Styron so that appropriate assessments may be conducted. Styron does not endorse or claim suitability of its products for specific medical applications and does not knowingly sell or sample its products or services for certain medical applications. It remains the responsibility of the medical device or pharmaceutical manufacturer to determine that the Styron product is safe, lawful, and technically suitable for the intended use.

No freedom from infringement of any patent owned by Styron or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer’s use and for ensuring that the Customer’s workplace and disposal practices are in compliance with applicable laws and other governmental enactments. **STYRON ASSUMES NO OBLIGATION OR LIABILITY FOR THE INFORMATION IN THIS DOCUMENT. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

If products are described as “experimental” or “developmental”: 1.) product specifications may not be fully determined; 2.) analysis of hazards and caution in handling and use are required; 3.) there is greater potential for Styron to change specifications and/or discontinue production; and 4.) although Styron may from time to time provide samples of such products, Styron is not obligated to supply or otherwise commercialize such products for any use of application whatsoever.

Our top priority is to provide the highest quality products and services, and to focus on the American Chemistry Council’s Responsible Care® initiative and safety in all of our facilities.

North America		Europe/Middle East	
U.S. & Canada:	1-888-STYRON ¹		+800 444 11 444
	1-989-633-1718	Germany:	+31-11567-2626
Mexico:	+1-800-441-4369		+8001811361
Latin America		Asia Pacific	
Argentina:	+54-11-4319-0100		+800-7776-7776
Brazil:	+55-11-5188-9000		+603-7965-5319
Colombia:	+57-1-219-6000		
Mexico:	+52-55-5201-4700		

www.styron.com

© 2014 Styron LLC, Styron HoldCo B.V., and subsidiaries

