



WANHUA CHEMICAL (NINGBO) CO LTD
39 Huandao Road (North), Daxie Development Zone
NINGBO, ZHEJIANG 315000 China



FR2827(##)

Polycarbonate (PC), pellets

(##) - May be followed by 1 or 2 suffix letters from A-Z

可燃性	值	测试方法
UL 阻燃等级		UL 94
1.5 mm, ALL	V-2	IEC 60695-11-10, -20
3.0 mm, ALL	V-0	
灼热丝易燃指数		IEC 60695-2-12
1.5 mm	960 °C	
3.0 mm	960 °C	
热灯丝点火温度		IEC 60695-2-13
1.5 mm	875 °C	
3.0 mm	850 °C	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
1.5 mm	PLC 2	
3.0 mm	PLC 2	
高电弧燃烧指数(HAI)		UL 746A
1.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 3	UL 746A
高电压电弧起痕速率 (HVTR)	PLC 2	UL 746A
热性能	值	测试方法
RTI Elec		UL 746B
1.5 mm	80.0 °C	
3.0 mm	80.0 °C	
RTI Imp		UL 746B
1.5 mm	80.0 °C	
3.0 mm	80.0 °C	
RTI		UL 746B
1.5 mm	80.0 °C	
3.0 mm	80.0 °C	