

Model FR6005 UV + (z)(f2)

File Number: E41613



COMPANY

Covestro Deutschland AG [PC Resins]
Chempark
Gebaeude B207
Leverkusen, 51368 Germany

MODEL INFO

FR6005 UV + (z)(f2)
Polycarbonate (PC) "Makrolon", impact modified, furnished as pellets
+ – Material designations may be followed by a six digit numerical code denoting color.
(z) – Material designation and color code may be followed by up to three letters and/or three numbers (does not include grades which are separately recognized with above material designation and suffix)
(f2) – Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL.

FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability		ANSI/UL 94
1.5 mm, Color: ALL	V-0	
3.0 mm, Color: ALL	V-0	
ISO/IEC FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability		IEC 60695-11-10
1.5 mm, Color: ALL	V-0	
3.0 mm, Color: ALL	V-0	
Glow Wire Ignition Temperature (GWIT)		IEC 60695-2-13
1.5 mm	850 °C	
3.0 mm	900 °C	
Glow Wire Flammability Index (GWFI)		IEC 60695-2-12
1.5 mm	960 °C	

UL Solutions 的 Cookie

我们通过 Cookie 使内容和广告个性化，以便提供社交媒体功能并分析我们的流量。我们还与社交媒体、广告和分析合作伙伴来分享您使用网站的信息。[了解更多信息](#)

Cookie 设置

拒绝全部

接受全部 Cookie

3.0 mm	960 °C	
ELECTRICAL PROPERTIES	VALUE	TEST METHOD
Hot-wire Ignition (HWI)		UL 746A
1.5 mm	PLC 2	
3.0 mm	PLC 0	
High Amp Arc Ignition (HAI)		UL 746A
1.5 mm	PLC 0	
3.0 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 3	UL 746A
Dielectric Strength	31 kV/mm	ASTM D149
Volume Resistivity	1.0E+16 ohms-cm	ASTM D257/IEC 60093
THERMAL PROPERTIES	VALUE	TEST METHOD
Relative Thermal Index - Electrical Strength		UL 746B
1.5 mm	125 °C	
3.0 mm	125 °C	
Relative Thermal Index - Mechanical Impact		UL 746B
1.5 mm	105 °C	
3.0 mm	105 °C	
Relative Thermal Index - Mechanical Strength		UL 746B
1.5 mm	115 °C	
3.0 mm	115 °C	
Ball Pressure Temperature	134 °C	
PHYSICAL PROPERTIES	VALUE	TEST METHOD
UV Exposure & Water Immersion	f2	UL 746C

UL Solutions 的 Cookie

我们通过 Cookie 使内容和广告个性化，以便提供社交媒体功能并分析我们的流量。我们还与社交媒体、广告和分析合作伙伴来分享您使用网站的信息。[了解更多](#)

Report Date: 2015-07-17
Revision Date: 2024-04-19

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL Solutions' Follow - Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL Solutions' Follow - Up Service. Always look for the Mark on the product.

UL Solutions permits the reproduction of the material contained in Product iQ subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from Product iQ with permission from UL Solutions" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "©2025 UL LLC."



UL Solutions 的 Cookie

我们通过 Cookie 使内容和广告个性化，以便提供社交媒体功能并分析我们的流量。我们还与社交媒体、广告和分析合作伙伴来分享您使用网站的信息。 [了解更多](#)