

iq.ul.com

PROSPECTOR®[CLICK TO CONTINUE](#)

View additional material information including performance and processing data

The information presented on the UL Prospector datasheet was acquired by UL Prospector from the producer of the material. UL Prospector makes substantial efforts to assure the accuracy of this data. However, UL Prospector assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.

E121562

Component - Plastics

Guide Information

SABIC INNOVATIVE PLASTICS US L L C

AMERICAS - RESIN, 1 PLASTICS AVE, PITTSFIELD MA 01201-3662

357(f1)(w)(IC), 357M(f1)(w)(IC), 357U(f1)(w)(IC)

Polybutylene Terephthalate/Polycarbonate (PBT/PC) "Valox", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
BK	0.63	V-0	3	4	120	120	140
	1.0	V-0	3	4	120	120	140
ALL	1.5	V-0	3	3	120	120	140
	2.0	V-0	3	3	120	120	140
	3.0	V-0, 5VA	2	3	120	120	140

Comparative Tracking Index (CTI): 2

Dielectric Strength (kV/mm): 31

High-Voltage Arc Tracking Rate (HVTR): 4

Dimensional Stability (%): 0

Inclined Plane Tracking (IPT) kV: 3.5

Volume Resistivity (10^x ohm-cm): 16Surface Resistivity (10^x ohms/square): -

High Volt, Low Current Arc Resis (D495): 6

(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.

(w) - Recognition includes the use of surface dyes.

IC - Inclined Plane Tracking per UL746A, average time to track at 3.5 kV is 60+ minutes.

NOTE - Material designation may be followed by a color nomenclature consisting of either an alpha/numeric or numeric/alpha combination.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1977-11-18

Last Revised: 2019-08-22

© 2020 UL LLC

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.63	V-0 (BK)
			1.0	V-0 (BK)
			1.5	V-0 (ALL)
			2.0	V-0 (ALL)
			3.0	V-0, 5VA (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	1.0	960
			2.0	960
			3.0	960
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	1.0	775
			2.0	750
			3.0	725
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	125
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-1	kJ/m ²	-	-